




SYMBOL CARD 2SC

description Environmentally-friendly ECF boards (SBS), certified FSC®. Double blade coated on both sides with the same Satin finishing. Available in Premium White colour. The substances 450gsm, 500gsm and 580gsm are off-machine laminated.

range	size	grain	substance					
	72x102	LG	300	350	400	450	500	580
	102x72	SG	300	350	400			



Double coating
Bleached chemical pulp
Double coating

technical features
ref. standard/instrument
unit of measure

substance	thickness	roughness	stiffness Taber 15°	
ISO 536	ISO 534	ISO 8791-2	ISO 2493	
g/m ²	µm	ml/min	mN	
			long±15%	cross±15%
300 ± 5%	320 ± 5%	20 (max 30)	170	120
350 ± 5%	380 ± 5%	20 (max 30)	260	170
400 ± 5%	435 ± 5%	20 (max 30)	335	230
450 ± 5%	480 ± 5%	40 (max 80)	600	400
500 ± 5%	550 ± 5%	40 (max 80)	800	600
580 ± 5%	660 ± 5%	40 (max 80)	1150	830

Brightness - ISO 2470 (R457) - 104% ± 2
Relative Humidity 50% ± 5 ref. TAPPI 502-98

ecological features



The mark of responsible forestry

ELEMENTAL
CHLORINE
FREE
GUARANTEED



ACID FREE



ISO 9706



CE 94/62

notes

The product is completely bio-degradable and recyclable. Special runs available upon request.

The Company reserves the right to modify the technological features of the product in relation to market requirements.

The Symbol Card 2SC is excellent for packaging, covers, postcards, promotional material and similar applications. It's held in high regard for technical performances like stiffness and smoothness, and very good printability in both sides.

applications

Can be used without problems with the main printing systems: offset, blind embossing, hot foil stamping, thermography and screen-printing. For offset printing, the characteristics of the coating surfaces are comparable to our Symbol Card.

**printing
suggestions**

Good results can be expected with all the main converting process: cutting, die-cutting, scoring, glueing, varnishing and plastic lamination. In 90° folding we suggest to score until the 50% of the thickness, whereas the 180° folding must be the 70% of the thickness board.

**converting
suggestions**